# **RUST-OLEUM®**



## **FASTKOTE®**

## **DESCRIPTION AND USES**

FastKote<sup>®</sup> is a 100% solids aromatic polyurea floor coating for use in industrial and commercial facilities. Suggested for interior applications only.

## **PRODUCTS**

277495	Gray
277496	Tan
277497	Super Light Gray
277498	Safety Yellow
285122	Black
280972	Clear

## RECOMMENDED PRIMER

FastKote can be applied direct to properly prepared concrete or used over one of the following primers. If there is a moisture issue with the floor, then it must be primed with one of the TVB Primers.

- S6511 Penetrating Prime & Seal Primer
- TVB Water Based Topside Vapor Barrier
- TVB 100% Solids Topside Vapor Barrier
- TurboPrime™
- ECO Prime™

## COMPANION PRODUCT

280945 Durability Additive

### **PACKAGING**

FastKote is packaged in a carton containing a re-sealable flexible pouch (102 fl oz) and a container of Stabilizer/Tint (26 fl oz), yields one full gallon.

## **APPEARANCE**

High gloss

### PRODUCT APPLICATION

#### **SURFACE PREPARATION**

The concrete surface must be free of all dirt, grease, oil, fats, and other contamination. Remove surface contamination by cleaning with Pure Strength® 3599 Industrial

Cleaner/Degreaser, detergent, or other suitable cleaner. Rinse thoroughly with clean, fresh water and allowed to dry.

Note: The substrate must be completely dry prior to application of FastKote. Polyurea coatings are sensitive to moisture and can affect proper curing of the coating.

NEW, UNCOATED CONCRETE: New concrete must be allowed to cure for a minimum of 30 days before application. In addition to the aforementioned cleaning, the concrete must be further prepared by mechanical grinding or acid etch to remove all laitance and produce a suitable surface profile.

PREVIOUSLY COATED CONCRETE: Previously coated concrete must be in good sound condition with the existing coating tightly adhering to the concrete. In addition to the aforementioned cleaning the existing coating must be sanded to dull the finish and produce a slight surface profile. Remove

## **PRODUCT APPLICATION (cont.)**

all sanding dust by vacuum. Do not wipe the floor with denatured alcohol or other solvent. If wiping is necessary, use only urethane grade Methyl Ethyl Ketone (MEK).

#### **CONCRETE REPAIR**

All spalls and cracks must be chased out and repaired to ICRI standards using an appropriate Concrete Saver patching material.

#### **MIXING**

Both components and environment should be pre conditioned to a minimum of  $50^{\circ}$  F ( $10^{\circ}$  C) prior to use. Be sure the air and surface temperatures are at least  $5^{\circ}$  above the dew point. FastKote is moisture sensitive, so be sure the outside of the flexible pouch is dry and free of condensation.

Shake the container of Stabilized/Tint for one full minute before combining with the FastKote. Cut off the top of the flexible pouch above the zip lock seal to open. The components can be mixed in a separate container or mixed in the pouch. If mixing in the pouch, use care to ensure not damaging the pouch or getting it wrapped around the mixer shaft. After combining the components, power mix at 500-700 rpm for 2-3 minutes. Use an appropriate size mixer and use care to not entrain air into the coating while mixing. Once mixed, the material has a 6 month shelf life.

#### **APPLICATION**

Apply only when air, material and floor temperatures are between 50-90°F (10-32°C). Do not apply in direct sunlight or when temperature is rising. Be sure the substrate is completely dry.

Pour out only the amount of material to be used into a roller pan. Unused material can be saved in the pouch or the mixing container for up to 6 months provided it is properly sealed. Do not return unused material from the roller pan to the pouch or mixing container.

Use a % inch, lint free roller with a phenolic core to roll out the coating. Begin with rolling out a W or M pattern, then cross roll to fill in and smooth out the coating.

NOTE: The Safety Yellow will require a two coat application to achieve optimum hide.

#### **THINNING**

None required

#### **CLEAN-UP**

1

Methyl Ethyl Ketone (MEK).

#### **EQUIPMENT RECOMMENDATIONS**

ROLLER: Use a high quality % inch lint-free roller with a phenolic core.

BRUSH: Use a disposable natural fiber chip brush, 2-4 inch wide for cut in work.

| Form: CFFS-04 | Rev.: 090314



## **TECHNICAL DATA**

## **FASTKOTE®**

## PERFORMANCE CHARACTERISTICS

Tensile Strength (ASTM D412) 5,200
Compressive Strength (ASTM D695) 11,500
Elongation (ASTM D412) 75

## PERFORMANCE CHARACTERISTICS (cont.)

Hardness, Shore D (ASTM D2240) 84 Gloss (ASTM D523) @ 60° >95

Abrasion Resistance (ASTM D4060)

CS-17 Wheel, 1,000 g load, 1,000 cycles 29

## PHYSICAL PROPERTIES

Resin Type		Aromatic Polyurea		
Weight	Per Gallon	9.4 lbs/gal Clear (finish colors are slightly higher and varies with color)		
	Per Liter	1.1 kg Clear (finish colors are slightly higher and varies with color)		
Solids By Volume		100%		
Volatile Organic	Compounds	<10 g/l		
Practical Coverage Rate		400 sq. ft./gal.  Coverage rate can vary depending on the texture and porosity of the concrete		
Dry Times @ 72ºF and 50% Relative Humidity <sup>†</sup>	Recoat	2-12 hours*		
	Light traffic	3-6 hours		
	Full traffic	24 hours		
Shelf Life		18 months unopened 6 months once the Stabilizer/Tint has been added		
Safety Information		See MSDS		

Calculated values are shown and may vary slightly from the actual manufactured material.

## CHEMICAL RESISTANCE

Acetic Acid 100%	RC	Methanol	P	Sugar/H20	R	
	KC			•		
Acetone	R	Methylene Chloride	L -	Sulfuric Acid 10%	R	
Ammonium Hydroxide 50%	RC	Mineral Spirits	R	Sulfuric Acid >50%	RC	
Benzene	RC	Motor Oil	R	Toluene	R	
Brake Fluid	RC	MTBE	С	1, 1,1-Trichlorethane	С	
Brine saturated H2O	R	Muriatic Acid 10%	R	Trisodium Phosphate	R	
Chlorinated H2O	R	NaCl/H2O 10%	R	Vinegar/H2O 5%	R	
Clorox(10%) H2O	R	Nitric Acid 20%	RC	H2O 14 days at 82° C	R	
Diesel fuel	RC	Phosphoric Acid 10%	RC	Xylene	NR	
Gasoline	R	Phosphoric Acid 50%	NR			
Gasoline/5% MTBE	R	Potassium Hydroxide 10%	R	Chemical Resistance Key R=recommended/little or no visible damage RC=recommended conditional/some effect, swelling or discoloration C=Conditional/Cracking- wash within one hour of spillage to avoid effects NR=Not recommended		
Gasoline/5% Methanol	R	Potassium Hydroxide 20%	R, Dis			
Hydrochloric Acid 20%	R	Propylene Carbonate	RC			
Hydrofluoric Acid 10%	RC	Skydrol	RC			
Hydraulic fluid (oil)	RC	Sodium Hydroxide 25%	R			
Isopropyl Alcohol	R	Sodium Hydroxide 50%	R. Dis			
Jet Fuel (JP-4)	R	Sodium Hypchlorite 10%	RC	Dis=Discolorativ		
Lactic Acid	RC	Sodium Bicarbonate	R	DIS-DISCOIDIALIY		
MEK	NR	Stearic Acid	R			

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Phone: 877•385•8155 www.rustoleum.com/industrial Form: CFFS-04 Rev.: 090314

<sup>&</sup>lt;sup>†</sup> Dry times will be increase if temperatures are less than 65° F (18°C) and /or Relative Humidity is less than 50%.

<sup>\*</sup> If 12 hour recoat time has elapsed, the coating must be sanded prior to recoating.