TECHNICAL DATA

CM-02

RUST-OLEUM[®]

COMMERCIAL

CV740 SYSTEM RUST PREVENTIVE ENAMEL

DESCRIPTION AND USES

The CV740 System Rust Preventive Enamels are designed for indoor and outdoor steel surfaces in mild to moderate environments. Excellent resistance to general weathering, salt air, mild chemical fumes and light abrasion. Not for use on galvanized steel.

If desired, the CV740 System Rust Preventive Enamels can be applied direct-to-metal (DTM), however optimal corrosion protection is achieved when the finish coat is used in conjunction with one of the recommended primers.

This product complies with USDA FSIS regulatory sanitation performance standards for food establishment facilities. This coating is impervious to moisture and easily cleaned and sanitized.

MPI #9, #48, #96 Certified*

PRODUCTS

PRIMERS

1-Gallon	Description	
255617	White Primer	
255610	Red Primer	

FLAT FINISH

1-Gallon	Description
255609	Flat Black

HIGH GLOSS FINISH

1-Gallon	Description
255611	Black
261959	Safety Blue
255616	Safety Yellow
255615	Safety Red
255613	Navy Gray
255612	Forest Green
255614	White
261956	Silver Gray
261957	Dunes Tan

HIGH GLOSS TINT BASES

1-Gallon	5-Gallon	Description
255621		Red
255620		Yellow
255618	286906	Masstone
255619	286908	Pastel
261961	286909	Deep

PRODUCTS (CONT.)

SATIN FINISH

1-Gallon	5-Gallon	Description	
282727	282737	Navy Gray	
282728	282738	Black	
282729	282739	White	
282730	282740	Silver Gray	
282732	282741	Dunes Tan	

SATIN FINISH TINT BASES

1-Gallon	5-Gallon	Description
282733	282742	Pastel
282734	282743	Deep
282736	282744	Masstone

PRODUCT APPLICATION

SURFACE PREPARATION

ALL SURFACES: Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with Pure Strength[®] Cleaner/Degreaser, item #3599402, commercial detergent or other suitable cleaner. Rinse thoroughly with fresh water and allow to fully dry. All surfaces must be dry at time of application.

STEEL: Hand tool (SSPC-SP-2) or power tool (SSPC-SP-3) clean to remove all loose rust, mill scale, and deteriorated previous coatings. If abrasive blasting cleaning is used, then two coats of recommended primer is required. See the primer Technical Data Sheet for more information.

PREVIOUSLY COATED: Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy finishes should be scarified by sanding to create a surface profile. The 7400 System Enamels are compatible with most coatings, but a test patch is suggested.

APPLICATION

Apply only when air and surface temperatures are between 32-100°F (0-38°C) and surface temperature is at least 5°F (3°C) above the dew point.

EQUIPMENT RECOMMENDATIONS

BRUSH: Use a good quality natural or polyester bristle brush.

ROLLER: Use a good quality natural or polyester cover. Use a short nap roller for smooth surfaces, and a medium nap roller for rough surfaces.

AIR-ATOMIZED SPRAY:

Method	Fluid Tip	Fluid Delivery	Atomization
Pressure	0.055-0.070	16 oz./min.	25-60 psi
Siphon	0.055-0.070	_	25-60 psi
HVLP (var.)	0.043-0.070	8-14 oz./min.	60-90 psi*

*10 psi maximum at tip

* Refer to the MPI website for the most current listing of MPI certified products.

TECHNICAL DATA

RUST-OLEUM"

COMMERCIAL

CV740 SYSTEM RUST PREVENTIVE ENAMEL

PRODUCT APPLICATION (cont.)

AIRLESS SPRAY (HIGH GLOSS):

Pump RatioFluid PressureFluid TipFilter Mesh30:11,600-2,400 psi0.013-0.017100

AIRLESS SPRAY (ALL OTHERS):

Pump Ratio	Fluid Pressure	Fluid Tip	Filter Mesh
30:1	1,600-2,400 psi	0.013-0.019	60

PRODUCT APPLICATION (cont.)

THINNING

BRUSH/ROLLER: Normally not required.

AIR-ATOMIZED SPRAY: 333402 Thinner: Use up to 15% by volume.

AIRLESS SPRAY: 333402 Thinner: Normally not required. If needed use up to 5% by volume.

CLEAN-UP

333402 Thinner or Acetone.

PHYSICAL PROPERTIES

		GLOSS FINISHES	SATIN FINISHES	PRIMERS
Resin Type			Modified Alkyd	
Pigment Type		Varies w	ith color	Titanium Dioxide, Red Iron Oxide
Solvents		Exen	npt halogenated and hydrocar	bon solvents
Weight	Per Gallon	9.0-10.4 lbs.	11.0-12.3 lbs.	12.1-12.2 lbs.
	Per Liter	1.1-1.2 kg	1.3-1.5 kg	1.5 kg
Solids	By Weight	46.0-54.8%	52.6-58.0%	59.5-62.0%
	By Volume	46.6-48.0%	43.9-48.6%	44.0-48.0%
Volatile Organic Compou	unds	<100 g/l (0.83 lbs./gal.)	<100 g/l (0.83 lbs./gal.	<100 g/l (0.83 lbs./gal.)
Recommended Dry Film Thickness (DFT) per Coa		1.5-2.5 mils (37.5-62.5µ)	1.5-2.5 mils (37.5-62.5µ)	1-2 mils (25-50µ)
Wet Film to Achieve DFT (Unthinned material)		3.5-5.5 mils (87.5-137.5µ)	3.5-5.5 mils (87.5-137.5µ)	2-4 mils (50-100µ)
Theoretical Coverage at 1 mil DFT (25µ)		750-770 sq. ft./gal. (18.5-18.9 m²/l)	700-780 sq.ft./gal. (17.2-19.2m²/l)	705-770 sq. ft./gal. (17.3-18.9 m²/l)
Practical Coverage at Recommended DFT (ass material loss)	200-400 sq. it./gai. 240-440 sq.it./gai. 300-000 s		300-650 sq. ft./gal. (7.4-16.0 m²/l)	
Dry Times at 70-80°F	Tack-free	4-6 hours	4-6 hours	4-6 hours
(21-27°C) and 50% Relative Humidity	Handle	8-12 hours	8-12 hours	8-12 hours
Relative Humidity	Recoat	24 hours	24 hours	24 hours
Dry Heat Resistance		200°F (93°C)	200°F (93°C)	200°F (93°C)
Shelf Life		5 years	5 years	5 years
Safety Information		See MSDS		

Calculated values may vary slightly from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation 11 Hawthorn Parkway Vernon Hills, Illinois 60061 An RPM Company

Phone: 877•385•8155 www.rustoleum.com/industrial